

# CSL 502A

## Industrial Silicone Sealant/Adhesive

### FEATURES

- Excellent sealant/adhesive for industrial use
- Provide permanently flexible bond or seal
- Excellent adhesion to glass, metal, porcelain, ceramic, wood, most plastics and many other non-porous substrates

### PRODUCT DESCRIPTION

CSL-502A is a one-part, moisture curing RTV (Room Temperature Vulcanizing) silicone sealant/adhesive designed for industrial use. It cures to a strong, silicone rubber that maintains long term durability and flexibility.

CSL-502A is an excellent sealant and/or adhesive for many industrial applications where a long term, permanently flexible bond or seal is required. Such applications include:

- Formed in-place gaskets for junction box covers
- Adhering appliance trim and sealing appliance parts
- Attaching name plates, letters and signs
- Sealing joints in ductwork
- Sealing truck trailers, cabs, marine portholes and cabins

### INSTALLATION

CSL-502A is ready-to-use and requires no mixing or additives. The cure mechanism begins as soon as the sealant comes in contact with air.

At 25°C (77°F) and 50% relative humidity (RH), the sealant will “skin” within 15 minutes and fully cure in 24 hours (1/8” bead), reaching its maximum adhesion in 7 days. Higher humidity accelerates cure, and curing time is increased with the thickness of the sealant. In applications where partial or total confinement of sealant is prevalent, the time required for proper cure is generally lengthened by the degree of confinement. Tooling, if necessary, should be done before “skinning” takes place. Surfaces should be clean and dry. Apply sealant to prepared surface in a uniform thickness.

A 15-30 mil glue line gives best adhesion. For sealing, apply CSL-502A into the joint so that full contact is made between sealant and surface. Priming is normally not required for applications to non-porous surfaces. Applying a small trial bead and allowing 7 days for maximum adhesion to occur can easily test unprimed adhesion. If primer is required consult CSL-944 product sheet or contact manufacturer.

### COLORS

CSL-502A standard colors are Clear, White, Grey, Aluminum, Black and Yellow. Special colors are available on request.

### PACKAGING

CSL-502A is available in 300 ml (10.2 fl. oz.) caulking cartridges packaged in cartons of 20 cartridges, 2.5 US gallon cans, 5 US gallon pails and 200 Litre drums.

### STORAGE

CSL-502A when stored in original unopened container at or below 32°C (90°F) has a life of 12 months from date of shipment.

### SAFETY PRECAUTIONS

CSL-502A releases small amounts of acetic acid during cure. Adequate ventilation should be provided with the extensive use of this sealant. On direct contact, uncured sealant may irritate eyes. Flush well with water and call a physician. See Material Safety Data Sheet available on this product.

### USDA STATUS

CSL-502A Clear, White and Aluminum are authorized by the US Department of Agriculture for use in meat and poultry plants.



## WARRANTY

CSL Silicones Inc. warrants that its products will meet its specifications. CSL shall in no event be liable for incidental or consequential damages. Except as expressly stipulated, CSL's liability, expressed or implied, is limited to the stated selling price of any defective goods.

Data is subject to change without notice and it is therefore recommended that this information not be used for specification writing. For additional information on specific applications, contact the manufacturer.

## Typical Properties

These values are not intended for use in preparing specifications

### UNCURED

|  |                              |
|--|------------------------------|
| Type   | 100% silicone, one-part RTV  |
| Appearance                                   | Smooth, non-slump paste      |
| Specific Gravity                             | 1.02                         |
| Slump/Sag                                    | Nil                          |
| Extrusion Rate (3.2mm (1/8") orifice, 90psi) | 200 g/min.                   |
| Application Temperature Range                | -18°C to 50°C (0°F to 120°F) |
| Cure System                                  | Acetoxy, Moisture Cure       |
| Skin-Over Time at Standard Conditions*       | 15 min.                      |
| Cure Time at Standard Conditions*            | 24 hr.                       |

### CURED AT STANDARD CONDITIONS\* FOR 7 DAYS

|   |                                   |
|---|-----------------------------------|
| Durometer Hardness (ASTM D2240, Shore A)                        | 20 points                         |
| Tensile Strength (ASTM D412)                                    | 12.3 kg/cm <sup>2</sup> (175 psi) |
| Elongation at Break (ASTM D412)                                 | 400%                              |
| Tear Resistance (ASTM D624, Die B)                              | 2.9 kN/m (16 ppi)                 |
| Thermal Expansion Coefficient<br>(0°C to 100°C / 32°F to 212°F) | 9.3 x 10 <sup>-4</sup> cm/°C      |
| Useable Temperature Range                                       | -62°C to 232°C (-80°F to 450°F)   |
| Dielectric Strength (ASTM D149)                                 | 550 V/mil (217kV/cm)              |
| Volume Resistivity (ASTM D257)                                  | 1.5 x 10 <sup>15</sup> ohm.cm     |
| Dissipation Factor, 100 Hz to 100 kHz<br>(ASTM D150)            | 0.0015                            |
| Dissipation Constant, 100 Hz to 100 kHz<br>(ASTM D150)          | 2.80                              |

\*Standard Conditions are 25°C (77°F) and 50% relative humidity

ISO 9001:2008 Registered

Contact CSL Silicones Inc. for the distributor nearest you.

144 Woodlawn Rd. West  
Guelph, ON N1H 1B5  
Canada

tel: +1 (519) 836-9044  
fax: +1 (519) 836-9069  
web: [www.csilsilicones.com](http://www.csilsilicones.com)  
e-mail: [info@csilsilicones.com](mailto:info@csilsilicones.com)

© 2010 CSL Silicones Inc.  
All rights reserved.

"CSL", "Si-COAT", "Technology that Sticks", the CSL logo and the Si-COAT logo are trademarks or registered trademarks of CSL Silicones Inc. in Canada, the USA and/or other countries.

Printed in Canada.

