

CSL 504

Hi-Temp Silicone Rubber Gasket Material

FEATURES

- Unaffected by extreme temperatures from -60°C to 315°C (-76°F to 600°F)
- Gasket will remain permanently flexible
- Provides excellent resistance to vibration and shock

PRODUCT DESCRIPTION

CSL-504 is a one-part, moisture curing RTV (Room Temperature Vulcanizing) silicone rubber that cures to a tough rubber gasket. It is specifically formulated to be used as a formed-in-place gasket where operating temperatures up to 315°C (600°F) are maintained.

Typical applications include:

- Water pump and compressor gaskets
- Appliance gaskets
- Ductwork gaskets
- Electrical insulation
- Air conditioner and humidifier gaskets
- Fireplace seals
- High temperature spacers

COLORS

CSL-504 is available in Black only.

PACKAGING

CSL-504 is available in 300 ml (10.2 fl. oz.) caulking cartridges packaged in cartons of 20 cartridges, 2.5 US gallon cans, 5 US gallon pails and 200 Litre drums.

STORAGE

CSL-504 when stored in original unopened container at or below 32°C (90°F) has a shelf life of 12 months from date of shipment.

ISO 9001:2008 Registered

Contact CSL Silicones Inc. for the distributor nearest you.

144 Woodlawn Rd. West
Guelph, ON N1H 1B5
Canada

tel: +1 (519) 836-9044
fax: +1 (519) 836-9069
web: www.cslsilicones.com
e-mail: info@cslsilicones.com

© 2010 CSL Silicones Inc.
All rights reserved.

"CSL", "Si-COAT", "Technology that Sticks", the CSL logo and the Si-COAT logo are trademarks or registered trademarks of CSL Silicones Inc. in Canada, the USA and/or other countries.

Printed in Canada.

SAFETY PRECAUTIONS

CSL-504 releases small amounts of acetic acid during cure. Adequate ventilation should be provided with the extensive use of this sealant. On direct contact, uncured sealant may irritate eyes. Flush well with water and call a physician. See Material Safety Data Sheet available on this product.

WARRANTY

CSL Silicones Inc. warrants that its products will meet its specifications. CSL shall in no event be liable for incidental or consequential damages. Except as expressly stipulated, CSL's liability, expressed or implied, is limited to the stated selling price of any defective goods.

Data is subject to change without notice and it is therefore recommended that this information not be used for specification writing. For additional information on specific applications, contact the manufacturer.

Typical Properties

These values are not intended for use in preparing specifications

UNCURED

Type	100% silicone, one-part RTV
Appearance	Smooth, non-slump black paste
Specific Gravity	1.14
Slump/Sag	Nil
Extrusion Rate (3.2mm (1/8") orifice, 90psi)	150 g/min.
Application Temperature Range	-18°C to 50°C (0°F to 120°F)
Cure System	Acetoxy, Moisture Cure
Skin-Over Time at Standard Conditions*	10 min.
Cure Time at Standard Conditions*	24 hr.

CURED AT STANDARD CONDITIONS* FOR 7 DAYS

Durometer Hardness (ASTM D2240, Shore A)	25 points
Tensile Strength (ASTM D412)	14.0 kg/cm ² (200 psi)
Elongation at Break (ASTM D412)	400%
Tear Resistance (ASTM D624, Die B)	4.0 kN/m (22 pli)
Useable Temperature Range	-60°C to 315°C (-76°F to 600°F)
Shrink Factor	Nil

*Standard Conditions are 25°C (77°F) and 50% relative humidity

